PRESSIZA 104 PERFORMANCE GUIDE

pressiza

Features

- Matte finished opaque white polypropylene synthetic material with the look and feel of paper and the moisture resistance of a film
- Specifically engineered for use in dye based on demand inkjet printers
- It couples good inkjet print quality with fast ink drying time for applications requiring variable information in conjunction with full color graphics
- Not recommended for flexo printing
- High performance, clear permanent emulsion acrylic pressure sensitive adhesive with balanced adhesion to a wide variety of substrates, including low surface energy plastics, engineering grade plastics, bare, coated, or painted metals, including powder coat and enamel paints
- Bleached supercalendered kraft stock featuring high internal strength, toughness, and tear resistance

Face

Caliper 0.0030 +/- 10% inches

Adhesive

Thickness	0.0010 +/- 10% inches
Peel Adhesion	Stainless Steel: 32 oz/inch

Temperature Ranges

Minimum Application +50° F (10° C)

Service Ranges -40° F to +302° F (-40°C to +150°C)

Suggested applications

It features medium tack and excellent chemical and UV resistance for outdoor industrial applications.

Ideally suited for marginal punching, perforating, and fanfolding.

Important:

This adhesive compositionally complies with Title 21 Code of Federal Regulations (C.F.R.) Section 175.105 ("Adhesives"). Compliance with this regulation permits the use of this adhesive in applications provided adhesive is separated from food by a functional barrier or 1) with dry food, the quantity of the adhesive does not exceed the limits of good manufacturing practice, or 2) with fatty and aqueous foods, the quantity of the adhesive that contacts the food does not exceed the trace amount at seams and at the edge exposure between packaging laminates that may occur within the limits of good manufacturing practice.

Liner

Caliper 0.0032 +/- 10% inches

Basis Weight 57.7# per ream +/- 10% (24" x 36" 500 sheets)

Shelf Life

Unless specified otherwise in this document, one year when stored at 72°F at 50% RH

This information is confidential, and restricted for the internal use of RSI México customers for informative purposes, and can not be reproduced or communicated to third parties without our written authorization.

TIJUANA: (664) 215.0679 **PUEBLA:** (222) 225.6594

HERMOSILLO: (662) 369.7306 comunicacion@rsimexico.com

